

Typical Analysis : loway H+

SAE	32	68	1732	1768
- density at 15 °C :	0.923	0.930	0.878	0.887
- visco. at 40°C / cSt :	32	68	32	68
- visco. at 100°C / cSt :	4.8	6.9	5.2	8.7
- viscosity index :	40	30	98	98
- flash point °C :	170	180	195	205
- pour point °C :	- 27	- 21	- 27	- 21
- T.B.N. mg KOH/g :	-	-	1.0	1.0
- colour :	7.5	8.0	1.0	2.0