

Typical analysis :

NLGI	00	0	2	3
• Colour	: Amber	Amber	Amber	Amber
• Soap type	: Lithium	Lithium	Lithium	Lithium
• Penetration at 25°C 60 strokes	: -	-	265-295	220-250
• Penetration loss after 100.000 strokes/ %max	: -	-	10	10
• Dropping point °C min	: >160	180	185	185
• Application range °C	-40 / +100	-20 / +120	-20 / +140	-20 / +140

EP properties

• 4 ball weld load/kg	: 240	280	230	230
-----------------------	-------	-----	-----	-----

Base oil specifications

• Viscosity at 40°C/ cSt	: 40	220	100	100
• Viscosity at 100°C/ cSt	: -	-7.8	7.8	7.8