

Typical analysis :

NLGI	2
• Colour	: Dark amber
• Soap type	: li-complex
• penetration at 25°C	:
60 strokes	275
• 10.000 strokes	280
• Dropping point	: 300°C
• Application range	: -25 / +180°C
• Timken Load	: 50 lb
• Four ball weld load	: 300 kg
• Water resistance	: 1-90
• Oxidation stability	: -
• Bars / drop 100 hr	: 0.4

Mineral oil specs:

• Viscosity at 40°C	: 160 cSt
• Viscosity at 100°C	: 15.5 cSt